

Milkana OOD

TEST REPORT

SCOPE OF WORK

IMPACT TESTING ON SAFETY GLAZING MATERIAL

REPORT NUMBER

G105241277CRT-001

ISSUE DATE

March 31, 2023

SGCC#

NA

PAGES

3

DOCUMENT CONTROL NUMBER

GFT-OP-10a (21-June-2019)

© 2019 INTERTEK



TEST REPORT:

Order No.: G105241277
Control No.: CRT2302091038-001

Report Issue Date: March 31, 2023
Authorization Date: March 13, 2023
Test Date: March 14, 2023

REPORT NO.: G105241277CRT-001
Rendered to: Nikolay Momchilov
Milkana OOD
6A Gena Dimitrova Str.
5800 Pleven
Bulgaria

Report on: Impact Testing on Safety Glazing Material

- 1 Sample Rec Date: February 9, 2023
- 2 SGCC No.: NA
- 3 Licensee: Milkana
- 4 Sample Size(s): 34"x76" 4mm Tempered Transparent Glass
- 5 Presence of Metalized Coating: No
- 6 All test specimens were received intact and in fair condition unless otherwise noted below.
- 7 All test specimens were destroyed by test or by our personnel and have been disposed of as trash.
- 8 Designated impact specimens were impacted once from the select drop height unless noted otherwise.

9 The specimens were evaluated in accordance with the following standards:

ANSI Z97.1-2015, For safety glazing materials used in buildings - safety performance

specifications and methods of test, American National Standard

CPSC 16 CFR 1201, Safety Standard for Architectural Glazing Materials, Consumer Product

Safety Commission (Version: 2012; Source: 42 FR 1441, Jan. 16, 1977)

CAN/CGSB 12.1-2022, Safety Glazing, National Standard of Canada

Impact Distance

Specimen No.	Test Standard	Thickness; Inches	at Which Disintegration Occurred; Inches	Weight of Largest ten Particles; Grams	Maximum Weight Permitted; Grams	Pass or Fail?
10	Results: Drop Class Height = A					
1	ANSI/CPSC/CGSB	0.151	48	23	62	PASS
2	ANSI/CPSC/CGSB	0.152	48	11	62	PASS
3	ANSI/CPSC/CGSB	0.151	48	18	62	PASS
4	ANSI/CPSC/CGSB	0.151	48	14	62	PASS


Comments: No comments

Reviewed By: Jeremy N. Downs, P.E.

Title: Senior Staff Engineer

Signature:

Date: 3/31/2023



Completed By: Russell Mantey

Title: Associate Engineer

Signature:

Date: 3/27/2023

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

IMAGE OF LABEL:

Sample#: 1

